



www.zetagi.it

**zetagi**

**Veneziani**

## WOOD PROTECTION

Issued 25.01.2012

### 1. Product name

**HTP Primer 210 code 171280**

### 2. Description

Water based one component primer for furniture protection and indoor wood refinishing.

### 3. Main features

Easily roughened by sandpaper; to be recoated by Holzfreund HTP Finish 210 flat code 171310.

Store the product in cans not containing metals such as iron, copper, zinc, aluminum and their alloys.

### 4. Recommended use

Furniture protection and indoor wood refinishing.

### 5. Technical data

Type	Internal method	Standard	Meas. unit	T Ref.	Value
<b>Specific gravity</b>	MS 018	ASTM D1475 ISO 2811-1	kg/dm <sup>3</sup>	23 °C	1,02 ± 0,05
<b>Solid content</b>		UNI EN ISO 3251	% p/p		34 ± 2
<b>Viscosity</b> Brookfield spindle 3 0.5 RPM	MS 007		mPas	23 °C	1000-2000*

### 6. Application data

**Color:** clear.

**Suggested DFT:** 40 - 60 µm.

**Theoretical consumption:** 100 - 150 g/m<sup>2</sup>.

**Practical spreading rate:** roughly 30% lower than the theoretical by airless application \*\*.

### 7. Application method

**Equipment:** airmix spray or electrostatic airless.

Suggested nozzle pressure 3.5 bar, pump ratio 1:30, pumps fitted by pre-atomizers and thin nozzles (9:40).

**Thinning:** up to 5% potable water depending on surface type and application method.



www.zetagi.it

**zetagi**

 **Veneziani**

## WOOD PROTECTION

### Drying time:

- Touch dry approx. 20'-40' at 23°C and 50% RH
- Hard dry approx. 24 h at 23 °C and 50% RH. In tunnel, oven or shelves, with T up to 35°C, the time can be reduced to 3-4 h.
- Stacking: the painted objects can be stacked vertically with suitable spacers about 48 hours after application. The process can be accelerated by drying in a tunnel for at least 2 hours, at progressive room temperature, up to a temperature of 35 °C.

**Number of coats:** 1 or 2 coats as described above.

**Application conditions:** application suggested between 15°C and 35°C, RH<70% and good ventilation.

### Suggested paint system:

- HTP 210 Primer W, code **171280**
- Steel wool roughening after 24 h
- HTP 210 Finish Flat W, code **171310**

### 8. Available colors

Clear

### 9. Storage indications

Shelf life: 12 months, provided the cans are kept sealed and undamaged, into a cool and dry place with temperature between 5 and 35°C.

Susceptible to frost damage.

### 10. Available packing

Standard packing 1, 4 and 25 kg. For different needs, please contact us.

### 11. Safety precautions

For professional use only. For health and safety information, please refer to the relevant Material Safety Data Sheet.

### 12. Notes, warnings and other information

Given the large number of factors that influence the painting process and our inability to control the use of the product itself, we can accept no responsibility for the final result.

\* parameters subject to testing for each batch.

\*\* indicative value, as it is dependent on numerous factors unrelated to the product, such as the size of the object, the conditions of the surface, the type and conditions of application

NB: the product conforms to Law Decree 27 March 2006 n.161;

It belongs to category i) High performance one component paints

VOC value lower than legal limit

VOC legal limits are 140 g/l from 01/01/2010.



[www.zetagi.it](http://www.zetagi.it)

**zetagi**

 **Veneziani**

## WOOD PROTECTION

*This Product Data Sheet has been written according to UNICHIM 1633 method*

*The information in this data sheet about the use of our products are based on our present scientific knowledge and practice. Zetagi accepts no commitment and / or responsibility on the final result of the work with our products. It is the customer's responsibility to verify the suitability of our products for the intended use. All the products and the advice given are subject to our general conditions of sale which we recommend you to request and read carefully. This data sheet replaces and annuls the previous ones: it is the user's responsibility to ensure that this sheet is updated prior to using the product. This data sheet is a translation; the Italian text of this document shall prevail over any translation thereof.*