



WOOD PROTECTION

Issued 02.05.2012

1. <u>Product name</u> HOLZFREUND Primer "W" LONG LIFE Code 672051

2. Description

Water based one component finish for outdoor application, based on acrylic resins

3. Main features

Particularly suitable as a barrier primer for exotic and hard woods, which contain substances that may interfere with the film formation or with the dry film itself of waterborne coatings. It contains UV absorbers that, laying directly into the fiber of wood, ensure total protection. It nicely revives the wood grain and it has a good wetting of the wood pores. Its good thixotropy allows an homogeneous film formation. A light sandpapering of the wood before the paint application is recommended. Store the product in cans not containing metals such as iron, copper, zinc, aluminum and their alloys.

4. Recommended use

Suitable for the coating of wooden windows and doors, as described above.

5. <u>Technical data</u>

| Туре | Internal method | Standard | Meas. unit | T Ref. | Value |
|--|--------------------|--------------------------------|---------------|---------------|------------------|
| Specific gravity | MS 018 | ASTM D1475 ISO 28811-1;1997 | kg/dm³ | 23℃ | 1,02 ±0,05 |
| Solid content | | UNI EN ISO 3251 | % p/p | | 31 <u>+</u> 2 |
| Viscosity (Brookfield spindle 3 0.5 RPM) | MS 007 | | mPas | 23 <i>°</i> C | 35000- 45000* |

6. Application data

Color: clear. Suggested DFT: 50 - 60 μm. Theoretical consumption: 160 - 200 g/m². Practical spreading rate: roughly 30% lower than the theoretical by airless application **.

7. Application method

Equipment: airmix spray or electrostatic airless.

Suggested nozzle pressure 3.5 bar, pump ratio 1:30, pumps fitted by pre-atomizers and thin nozzles (9:40).

Thinning: up to 10% potable water depending on surface type and application method.



WOOD PROTECTION

Drying time:

- Touch dry approx. 25'-45' at 23 °C and 50% RH
- Hard dry approx. 24 h at 23 °C and 50% RH. In tunnel, oven or shelves, with T up to 35 °C, the time can be reduced to 3-4 h.

The process can be accelerated by drying in a tunnel for at least 2 hours, at progressive room temperature, up to a temperature of 35 °C.

Number of coats: 1 or 2 coats as described above, sandpapering between the two coats.

Application conditions: application suggested between 12 °C and 35 °C, RH<70% and good ventilation. The substrate must be perfectly clean and dry. Lower temperatures and high RH can stop the film formation.

8. <u>Available colors</u>

Clear

9. Storage indications

Shelf life: 12 months, provided the cans are kept sealed and undamaged, into a cool and dry place with temperature between 5 and 35° C. Susceptible to frost damage.

10. Available packing

Standard packing 25 and 60 l. For different needs, please contact us.

11. Safety precautions

For professional use only. For health and safety information, please refer to the relevant Material Safety Data Sheet.

12. Notes, warnings and other information

Given the large number of factors that influence the painting process and our inability to control the use of the product itself, we can accept no responsibility for the final result.

* parameters subject to testing for each batch.

** indicative value, as it is dependent on numerous factors unrelated to the product, such as the size of the object, the conditions of the surface, the type and conditions of application

NB: the product conforms to Law Decree 27 March 2006 n.161;

It belongs to category i) High performance one component paints VOC value lower than legal limit VOC legal limits are 140 g/l from 01/01/2010.

This Product Data Sheet has been written according to UNICHIM 1633 method



WOOD PROTECTION

The information in this data sheet about the use of our products are based on our present scientific knowledge and practice. Zetagi accepts no commitment and / or responsibility on the final result of the work with our products. It is the customer's responsibility to verify the suitability of our products for the intended use. All the products and the advice given are subject to our general conditions of sale which we recommend you to request and read carefully. This data sheet replaces and annuls the previous ones: it is the user's responsibility to ensure that this sheet is updated prior to using the product. This data sheet is a translation; the Italian text of this document shall prevail over any translation thereof.