



www.zetagi.it

zetagi

Veneziani

WOOD PROTECTION

Issued 07.02.2012

1. Product name

HOLZVERLACK ACRYLIC Series 3280000

2. Description

Two pack, coloured, polyurethane enamel based on acrylic resins

3. Main features

High chemical resistance, excellent flexibility, hard and highly resistant to weathering, limited loss of gloss, no yellowing.

The extra curing improves overall physical, chemical and mechanical strength.

4. Recommended use

As a finish coat for wood structures

5. Technical data

Type	Internal method	Standard	Meas. unit	T Ref.	Value
Specific gravity	MS 018	ASTM D1475 ISO 28811-1;1997	kg/dm ³	23 °C	0,93 ± 0,05
Solid content		UNI EN ISO 3251	% p/p		29 ± 2
Viscosity (DIN cup 4)	MS 013		Sec.	23 °C	20- 30 *

6. Application data

Finish: flat, 0-10 gloss , flat 10-20 gloss and flat 30-40 gloss - angle 60°(ISO 2813).

Color: shades on request

Suggested DFT: 40 - 70 µm.

Theoretical consumption: 150 - 250 g/m²

Practical spreading rate: roughly 30% lower than the theoretical by airless application **.

7. Application method

Equipment: airmix or airless.

Thinning: to application viscosity by Thinner for Polyurethanes code 901031 or Thinner RETRON "S" code 901032, or similar thinners.

Drying time:

- Touch dry approx. 30'-60' at 23 °C and 50% RH.
- Hard dry approx. 8 h at 23 °C and 50% RH.

Drying times vary according to DFT, thinning and environmental conditions.

Number of coats: 1 coat as described above.

Application conditions: application suggested between 10 °C and 30 °C, RH<70%, good ventilation, perfectly clean support, on top of a polyurethane primer.



www.zetagi.it

zetagi

 **Veneziani**

WOOD PROTECTION

Pot life: 6 h at 20°C. Data vary with thinning and temperature
Mixing ratio: 100:10 by weight with Curing Agent code 7208500

8. Available colors
Shades on request

9. Storage indications
Shelf life: 12 months, provided the cans are kept sealed and undamaged, into a cool and dry place with temperature between 5 and 35°C.

10. Available packing
Standard packing 25 Kg. For different needs, please contact us.

11. Safety precautions
For professional use only. For health and safety information, please refer to the relevant Material Safety Data Sheet.

12. Notes, warnings and other information
Given the large number of factors that influence the painting process and our inability to control the use of the product itself, we can accept no responsibility for the final result.

* parameters subject to testing for each batch.

** indicative value, as it is dependent on numerous factors unrelated to the product, such as the size of the object, the conditions of the surface, the type and conditions of application

NB: the product does not conform to Law Decree 27 March 2006 n.161:

It belongs to category e) Paints and Impregnating for indoor and outdoor wood finishes

VOC value lower than legal limit

VOC legal limits are 400 g/l from 01/01/2010.

To be used only for applications not ruled by Leg. Decree n. 161/2006

This Product Data Sheet has been written according to UNICHIM 1633 method

The information in this data sheet about the use of our products are based on our present scientific knowledge and practice. Zetagi accepts no commitment and / or responsibility on the final result of the work with our products. It is the customer's responsibility to verify the suitability of our products for the intended use. All the products and the advice given are subject to our general conditions of sale which we recommend you to request and read carefully. This data sheet replaces and annuls the previous ones: it is the user's responsibility to ensure that this sheet is updated prior to using the product. This data sheet is a translation; the Italian text of this document shall prevail over any translation thereof.