



www.zetagi.it

zetagi

Veneziani

WOOD PROTECTION

1. Product name

HOLZFREUND LASUR Impregnating W-MD Series 682000

2. Description

Water borne Lasur-impregnating in gel form, for exterior wood.

3. Main features

Product Formulated with special high quality water-soluble resins, it contains IPBC. This series has been specifically developed for the protective treatment of wood on the outside, it comes in the form of gel and allows it to be applied on even vertical supports without dripping. High hyding power and protective, it allows, in two hands, an effective treatment on non-stable supports dimensionally as gazebos, houses, pergolas etc ... The quality of the coating and reduced thickness allow easy maintenance in all those cases where the aesthetic and protective integrity of the wood It's requested. Bright, uniform colors, obtained with transparent iron oxides which, as well as not changing color through time, lengthen the life of the wood joinery as they are a very efficient absorbers of ultraviolet radiation, it ensures an excellent color harmonizing effect enhancing the natural beauty of wood. It can be over coated by water based and solvent based finishes.

Recommended use

Treatment of wood carpentries and shutter, beams, cladding, canopies in the usage class 2 and 3, not suitable for wood in continuous contact or immersed in soil and / or water.

4. Technical data

Type	Internal method	Standard	Meas. unit	T Ref.	Value
Specific gravity	MS 018	ASTM D1475 ISO 2811-1	kg/dm ³	23°C	1,02 ± 0,05
Solid content		UNI EN ISO 3251	% p/p		13 ± 2
Viscosity (cup DIN 4)	MS 013		Sec.	23°C	17-22*

5. Application data

Color: clear, ebony, dark oak, mahogany, chestnut, walnut, dark walnut, Douglas, honey, light walnut, larch, oak, walnut tan, green.

Theoretical consumption: 100-120 g/m², or 8-10 m²/kg depending on the type of support and the application methods.



www.zetagi.it

zetagi

Veneziani

WOOD PROTECTION

Practical spreading rate: the shape and properties of the substrate and wood moisture affect the consumption / yield. Accurate values for consumption must be obtained by applying trial coats in advance.

6. Application method

Thinning: product ready to use **Equipment:** brush.

Preparation: the substrate must be clean, free from dust, dry capable of holding paint, free from separating substances as wax, grease, silicone, resin etc, as well as tested for suitability for coating application. All defective coatings should be completely removed. Any grey denatured exposed timber surfaces must be thoroughly sanded back to clean, bright timber. Organic growths must be removed and infected surfaces should be treated with a suitable fungicidal solution.

Number of coats: 1 or 2 coat as described above.

Application conditions: Do not apply if there is a risk of rain, or when air / substrate temperatures are below 8°C or above 25°C, or if the relative humidity is above 80% during application or drying periods. Protect from frost and rain until dry. Failure to meet these requirements may adversely affect the drying, visual quality and durability of the finish.

Drying time: ready to handle in 20' - 40' at 23°C, 50% RH and good ventilation according to the type of wood. Stack the product through spacers, until total drying of the product, do not expose the objects outdoor before the full drying of the impregnating (24 hours, if the application conditions are adhered to).

Recoatable. minimum after 2 hours

Cleaning the work equipment: with water immediately after use.

7. Available colors

Ebony, dark oak, mahogany, chestnut, walnut, dark walnut, douglas, green, honey, light walnut, larch, oak, reddish walnut, other shade on request.

8. Storage indications

Store the product in cans not containing metals such as iron, copper, zinc, aluminium and their alloys. Shelf life: 8 months, provided the cans are kept sealed and undamaged, into a cool and dry place with temperature between 5 and 35°C. Susceptible to frost damage.

9. Available packing

Standard packing 1/5/25 liters; for different needs, please contact us.

10. Safety precautions

For professional use only. For health and safety information, please refer to the relevant Material Safety Data Sheet.



www.zetagi.it

zetagi

 **Veneziani**

WOOD PROTECTION

11. Notes, warnings and other information

Given the large number of factors that influence the painting process and our inability to control the use of the product itself, we can accept no responsibility for the final result. * parameters subject to testing for each batch.

NB: the product conforms to Law Decree 27 March 2006 n.161; It belongs to category f)
Impregnating non film-forming for wood VOC value lower than legal limit
VOC legal limits are 140 g/l from 01/01/2010.

This Product Data Sheet has been written according to UNI standard 11269

The information in this data sheet about the use of our products are based on our present scientific knowledge and practice. Zetagi accepts no commitment and / or responsibility on the final result of the work with our products. It is the customer's responsibility to verify the suitability of our products for the intended use. All the products and the advice given are subject to our general conditions of sale which we recommend you to request and read carefully. This data sheet replaces and annuls the previous ones: it is the user's responsibility to ensure that this sheet is updated prior to using the product.

This data sheet is a translation;